



## CENOSPHERE INDIA PVT. LTD.

2, St. George Gate Road, Hastings  
Agarwal House, 2nd Floor, Kolkata-700 022  
Phone : 91-33-2223 2930 / 2223 6255  
Fax : 91-33-2223 4490  
E-mail : info@cenosphereindia.com  
Web : www.cenosphereindia.com

### CIL30 LFE

#### CHEMICAL ANALYSIS :

SIO <sub>2</sub>	52 - 62 %
AL <sub>2</sub> O <sub>3</sub>	20 - 42 %
CAO	0.1 - 0.5 %
K <sub>2</sub> O	1.0 - 2.0 %
FE <sub>2</sub> O <sub>3</sub>	0.5 - 2.0 %
TIO <sub>2</sub>	0.8 - 1.3 %
MGO	1.0 - 2.5 %
NA <sub>2</sub> O	0.2 - 0.6 %
CARBON DIOXIDE	70 %
NITROGEN	30 %

#### PHYSICAL PROPERTIES :

SPECIFIC GRAVITY	0.75 - 0.85 G/CC
BULK DENSITY	350 - 450 KGS/CBM
HARDNESS (MOH)	5 - 6
COMPRESSIVE STRENGTH	180 - 280 KGS/CM <sup>2</sup> (1500 - 3000 PSI)
SHAPE	SPHERICAL
PACKING FACTOR	60 - 65 %
WALL THICKNESS	5 - 15 % OF SHELL DIAMETER
COLOUR	LIGHT GREY - LIGHT BUFF
MELTING POINT	1200 - 1400 DEG CELCIUS
THERMAL CONDUCTIVITY	0.11 WM-1K-1
PH IN WATER	6 - 7
MOISTURE	0.5 % MAX
LOSS ON IGNITION	2 % MAX
SINKERS	3 % MAX
OIL ABSORPTION	16 - 18 G/100G

#### SIEVE ANALYSIS :

+ 30 # (500 MICRON)	0 - 1 %
+ 60 # (250 MICRON)	0 - 5 %
+100 # (150 MICRON)	20 - 70 %
+150 # (106 MICRON)	50 - 80 %
+ 240 # (63 MICRON)	75 - 95 %
- 240 #	0 - 20 %